



AB-619 Series *(Styrene-Butadiene)*

Fabric Finish Red Sheet

GENERAL PROPERTIES

- Industrial SBR for gaskets

POLYMER

Styrene-Butadiene (SBR)

View Up To Date Info



◀ SCAN OR VISIT
[KOA.link/
AB-619](https://koi.link/AB-619)

Series	ASTM Specification (SI units)	Temperature Range	Specific Gravity (gr/cc)	Durometer	Tensile Strength (psi)	Elongation (%)
AB-619	D2000 : 1AA806Z1	-20° to 180°F (-29° to 82°C)	1.8	75 +/- 5	600 min.	100 min.

ASTM D2000 SPECIFICATION AND TESTS

	ASTM	Description	Value
	D395 (Method B)	Compression Set 22 hrs @ 70°C (158°F)	50% max.
	D573	Heat Aging 70 hrs @ 70°C (158°F)	Hardness: +/-15 Tensile (%): +/-30 max. Elongation (%): -50 max.

ADDITIONAL SPECIFICATIONS

Grade	Industrial
Finish	Fabric (both sides)
Powder	No
Color	Red

Item Number	Gauge x Width (in)	Avg. Length (Linear Ft./Roll)	Surface (sft)	Approx. Lbs./Roll
261-04-362	1/16 x 36	110	330	159
261-04-366	1/16 x 36	66.6	200	96
261-04-482	1/16 x 48	80	320	157
261-06-362	3/32 x 36	75	225	176
261-06-366*	3/32 x 36	42	126	99
261-06-482*	3/32 x 48	55	220	172
261-08-362	1/8 x 36	55	165	173
261-08-366	1/8 x 36	32	96	101
261-08-482	1/8 x 48	40	160	167
261-08-486	1/8 x 48	23.5	94	100
261-12-362*	3/16 x 36	40	120	185
261-12-366*	3/16 x 36	19.667	59	91
261-12-482	3/16 x 48	30	120	184
261-16-362	1/4 x 36	30	90	191
261-16-366	1/4 x 36	15.3	45.9	97
261-16-482	1/4 x 48	20	80	169

*Non-stocked size. Made to order with required number of rolls. Longer lead time applies. Contact Kuriyama Customer Service for details.

Maximum pieces per roll: 2 • Minimum piece length: 5' • Width tolerance: -0.5 / +1"

Material is within commercial sheet rubber gauge tolerances. The documentation for sheet rubber gauge tolerances is published on our website. Please ensure the product meets your application specification prior to order placement. Specifications are subject to change without notice. The website version prevails.

Total roll length may vary by ±10% for domestically manufactured (AB-619) Series.

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.