



SKIRT-SHIELD™ A+ (Natural Rubber)

Premium Orange Skirtboard

GENERAL PROPERTIES

- Abrasion resistant, ideal for both wet and dry materials
- Flexible
- Same premium DURASHIELD® A+ compound, supplied in cut-to-width sizes.

POLYMER

Natural Rubber (NR/CR)



View Up To Date Info



◀ SCAN OR VISIT
KOA.link/SS-A-PLUS

Series	ASTM Specification (SI units)	Temperature Range	Specific Gravity (gr/cc)	Durometer	Tensile Strength (psi)	Elongation (%)	Tear (lbs/in)
Skirt-Shield A+	D2000 : 4AA425A13B13F17	-40° to 180°F (-40° to 82°C)	1.03	40 +/- 5	2500 min. 3000 typical	500 min. 700 typical	180 typical

ASTM D2000 SPECIFICATION AND TESTS

ASTM	Description	Value
 DIN	DIN Abrasion Method 53516	Wet: 12 mm ³ Dry: 120 mm ³
	D2137 Cold Temperature	-40°C/°F min.
	D395 Compression Set (Method B) 22 hrs @ 70°C (158°F)	25% max.
	D573 Heat Aging 70 hrs @ 70°C (158°F)	Hardness: +10 Tensile (%): -25 max. Elongation (%): -25 max.

ADDITIONAL SPECIFICATIONS

Grade	Premium
Finish	Smooth
Powder	No
Color	Orange

Item Number	Gauge x Width (in)	Avg. Length (Linear Ft./Roll)	Surface (sft)	Approx. Lbs./Roll
153-16-044	1/4 x 4	50	--	23
153-16-064	1/4 x 6	50	--	33
153-16-084	1/4 x 8	50	--	45
153-24-044	3/8 x 4	50	--	33
153-24-064	3/8 x 6	50	--	49
153-24-084	3/8 x 8	50	--	66
153-32-044	1/2 x 4	50	--	44
153-32-064	1/2 x 6	50	--	66
153-32-084	1/2 x 8	50	--	88
153-32-104	1/2 x 10	50	--	115
153-32-124	1/2 x 12	50	--	139

Material is within commercial sheet rubber gauge tolerances.
The documentation for sheet rubber gauge tolerances is published on our website.
Typical values do not constitute a specification.
Please ensure the product meets your application specification prior to order placement.
Specifications are subject to change without notice. The website version prevails.
Total roll length may vary by ±10% for domestically manufactured (SKIRT-SHIELD A+) Series.

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.