



IM-S60 Series *(Silicone)*

Terracotta Red Sheet

GENERAL PROPERTIES

- Excellent resistance to extreme temperatures
- High tear resistance
- Low compression set
- Excellent resistance to UV, ozone, and weathering
- Resists most fluids encountered in general industrial applications

View Up To Date Info



◀ SCAN OR VISIT
KOA.link/IM-S60

POLYMER

Silicone Rubber

Series	ASTM Specification (SI units)	Temperature Range	Durometer	Tensile Strength (psi)	Elongation (%)
IM-S60	ASTM D2240	-80° to 450°F (-62° to 232°C)	60 +/- 5	800 typical	400 typical

ADDITIONAL SPECIFICATIONS

Grade	Industrial
Finish	Smooth
Powder	No
Color	Terracotta red

Item Number	Gauge x Width (in)	Avg. Length (Linear Ft. /Roll)	Surface (sft)	Approx. Lbs./Roll
861-04-362	1/16 x 36	50	150	61
861-08-362	1/8 x 36	50	150	122
861-08-482	1/8 x 48	50	200	164
861-16-362	1/4 x 36	50	150	245

The maximum temperature is for instantaneous and not continuons applications.
Material is within commercial sheet rubber gauge tolerances.
The documentation for sheet rubber gauge tolerances is published on our website.
Typical values do not constitute a specification.
Please ensure the product meets your application specification prior to order placement.
Specifications are subject to change without notice. The website version prevails.

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.