



IM-618 Series *(Styrene-Butadiene)*

Smooth Finish Red Sheet

GENERAL PROPERTIES

- Industrial blend SBR for gaskets

POLYMER

Styrene-Butadiene (SBR)

[View Up To Date Info](#)



◀ SCAN OR VISIT
[KOA.link/IM-618](https://koa.link/IM-618)

Series	ASTM Specification (SI units)	Temperature Range	Durometer	Tensile Strength (psi)	Elongation (%)
IM-618	ASTM D2240	-20° to 180°F (-29° to 82°C)	75 +/- 7	400 typical	220 typical

ADDITIONAL SPECIFICATIONS

Grade	Industrial
Finish	Smooth
Powder	No
Color	Red

Item Number	Gauge x Width (in)	Avg. Length (Linear Ft. /Roll)	Surface (sft)	Approx. Lbs./Roll
110-04-368	1/16 x 36	70	210	119
110-04-488	1/16 x 48	50	200	113
110-04-728*	1/16 x 72	70	420	233
110-06-368*	3/32 x 36	55	165	140
110-08-368	1/8 x 36	35	105	119
110-08-488	1/8 x 48	25	100	113
110-08-728	1/8 x 72	35	210	238
110-12-368*	3/16 x 36	50	150	254
110-12-488*	3/16 x 48	35	140	237
110-16-368	1/4 x 36	35	105	237
110-16-488	1/4 x 48	25	100	226
110-16-728*	1/4 x 72	20	120	271

*Non-stocked size. Made to order with required number of rolls. Longer lead time applies. Contact Kuriyama Customer Service for details.

Maximum pieces per roll: 1 • Width tolerance: -0 / +1" • Durometer tolerance: +/-7 points

Material is within commercial sheet rubber gauge tolerances.

The documentation for sheet rubber gauge tolerances is published on our website.

Typical values do not constitute a specification.

Please ensure the product meets your application specification prior to order placement. Specifications are subject to change without notice. The website version prevails.

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.