

The Chemical Guides in this section are offered as a general indication of the compatibility of the various materials used in ALFAGOMMA® hose with the chemicals and fluids listed. The basis for the ratings in this guide include actual service experience, the advice of various polymer suppliers, and the considered opinion of our rubber chemists. When in doubt, a sample of the compound should always be tested with the particular chemical it is to handle. Some of the variables that come into play in the resistance of a compound to chemical attack are:

1. Temperature of the Material Transmitted:

Higher temperatures increase the effect of chemicals on rubber compounds. The increase varies with the polymer and the chemical. A compound quite suitable at room temperature might fail very quickly at higher temperatures.

2. Service Conditions:

A rubber compound usually swells when exposed to a chemical. With a given percent of swell, the hose tube may function satisfactorily if the hose is in a static condition, but fail quickly if the hose is subject to flexing.

3. The Grade or Blend of the Rubber Compound:

Basic rubber polymers are sometimes mixed or blended together to enhance a particular property for a specific service. The reaction to a particular chemical blend of polymers may, therefore, be somewhat different from the reaction to the single ones. When in doubt, a sample of the compound should always be tested with the particular chemical it is to handle.

4. Alfagomma® hoses are produced using silicone free release agents.

GENERAL CHEMICAL RESISTANCE OF ALFAGOMMA® HOSE COMPOUNDS

ASTM Designation D1418-93	Common Name	Composition	General Properties
CIIR	Chlorobutyl	Chloro-Isobutene-Isoprene	Excellent resistance to high heat steam. Very good weathering resistance, low permeability to air. Good physical properties. Poor resistance to petroleum-based fluids.
CR	Neoprene	Chloroprene	Excellent weathering resistance. Flame retarding. Good oil resistance. Good physical properties.
CSM	Hypalon®	Chloro-sulfonated polyethylene	Excellent ozone, weathering and acid resistance. Good abrasion and heat resistance. Can be compounded for good oil resistance.
EPDM	EPM or EPDM	Ethylene-propylene-diene-terpolymer	Good general purpose polymer. Excellent heat, ozone and weather resistance. Not oil resistant.
NBR	BUNA-N or Nitrile	Nitrile-Butadiene	Excellent oil resistance. Good physical properties.
NR	Natural	Isoprene Rubber (Natural)	Excellent physical properties, including abrasion resistance. Not oil resistant.
SBR	SBR	Styrene-Butadiene Rubber	Good physical properties, including abrasion resistance. Not oil resistant.
UHMWPE	UHMWPE	Ultra-High Molecular Weight Polyethylene	Excellent resistance to a majority of existing chemicals. Meets FDA requirements for food and beverages.
XLPE	Cross Linked Polyethylene	Cross Linked Polyethylene	Excellent resistance to most solvents, oils and chemicals. Do not confuse with chemical properties of standard polyethylene.
	Synthetic Rubber	Synthetic Rubber	Black conductive synthetic rubber, excellent resistance to Biofuel based fluids.

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.

KEY TO CHEMICAL RESISTANT CHART

(all data based on +68°F (+20°C) unless noted)

E Excellent G Good F Fair C Conditional I Insufficient Data X Not Recommended No Data

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Acetaldehyde	E	C	F	E	X	F	X	E	E	X
Acetic Acid, glacial	G	F	C	G	X	C	X	E	E	X
Acetic Acid, 10%	G	E	E	E	E	G	F	E	E	E
Acetic Acid, 50%	G	F	E	E	F	X	F	E	E	F
Acetic Anhydride	C	G	E	G	X	F	X	E	E	X
Acetic Oxide (acetic anhydride)	G	G	E	G	X	F	X	E	E	X
Acetone	E	C	X	E	X	C	C	E	E	X
Acetone cyanohydrin	E	G	F	E	X	F	-	-	-	X
Acetonitrile	E	E	G	E	X	G	-	-	-	X
Acetophenone	G	X	X	E	X	C	X	E	E	X
Acetyl Acetone	E	X	X	E	X	X	X	-	-	X
Acetyl Chloride	X	X	C	X	X	X	X	-	-	X
Acetyl Oxide (Acetic Anhydride)	G	G	E	G	X	F	-	E	E	X
Acetylene	E	E	C	E	E	C	F	E	E	E
Acetylene Dichloride	F	X	X	C	X	X	X	-	-	X
Acetylene Terachloride	X	C	X	C	X	X	-	-	-	X
Acrolein	E	G	G	E	F	G	F	-	-	F
Acrylonitrile	X	X	C	E	X	C	F	E	E	X
Acrylic acid	-	X	G	X	X	X	-	-	-	X
Adipic acid	X	E	G	C	E	E	-	E	E	E
Air, +300°F	G	G	G	G	G	X	X	-	-	G
Alk-Tri	X	X	X	X	X	X	-	-	-	X
Allyl Alcohol	E	E	E	E	E	E	-	E	E	E
Allyl Bromide	X	X	X	X	X	X	-	-	-	X
Allyl Chloride	C	X	X	X	G	X	E	E	F	G
Alum (Aluminium Potassium Sulfate)	E	E	E	G	C	E	-	E	E	C
Aluminium Acetate	G	C	F	E	C	E	X	-	-	C
Aluminium Chloride	E	E	E	E	E	E	E	E	E	E
Aluminium Fluoride	E	E	E	E	E	E	E	E	E	E
Aluminium Formate	G	E	X	E	X	X	-	-	-	X
Aluminium Hydroxide	E	E	E	E	E	E	G	E	E	E
Aluminium Nitrate	E	E	E	E	E	E	E	-	-	E
Aluminium Sulfate	A	G	E	E	E	E	G	E	E	E
Alumus-Nh3-Cr-K	-	-	-	-	-	-	-	-	-	-
Amines-Mixed	-	C	X	G	X	C	G	-	-	X
Aminobenzene (Aniline)	E	X	C	C	X	X	X	E	E	X
Aminodimethylbenzene	G	X	F	C	C	X	-	-	-	C
Aminoethane (Ethylamine)	G	C	F	E	C	C	X	E	E	C
Aminoxylene	G	X	X	E	C	X	-	-	-	C
Ammonium Carbonate	E	E	C	E	C	E	E	-	-	C
Ammonium Chloride	E	E	E	E	G	E	E	E	E	G
Ammonium Hydroxide	G	E	E	E	C	G	X	E	E	C
Ammonium Nitrate	E	E	E	E	E	E	E	E	E	E
Ammonium Phosphate, Dibasic	E	E	E	E	E	E	E	E	E	E
Ammonium Sulfate	E	E	E	E	E	E	G	E	E	E
Ammonium Sulfide	E	E	E	E	C	E	G	E	E	C
Ammonium Thiosulfate	E	E	E	E	C	E	-	-	-	C
Amyl Acetate	G	X	X	C	X	C	X	E	E	X
Amyl Acetone	G	X	X	G	X	X	-	-	-	X
Amyl Alcohol	E	C	E	E	C	C	G	E	E	C
Amyl Bromide	X	X	X	C	X	X	-	-	-	X
Amyl Chloride	X	X	X	X	X	X	X	E	E	X
Amyl Ether	X	X	F	X	C	X	-	-	-	C
Amylamine	G	C	F	X	F	F	-	-	-	F
Anethole	X	X	X	X	X	X	-	-	-	X
Aniline	E	X	C	C	X	X	X	E	E	X

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Aniline Dyes	G	C	G	C	X	C	G	E	E	X
Aniline Oil	G	X	C	C	X	X	X	E	E	X
Animal Fats	C	C	F	C	E	X	X	E	E	E
Antimony Pentachloride	-	C	X	C	X	X	-	E	E	X
Aqua Regia	C	X	C	C	X	X	X	X	X	X
Argon	G	G	X	E	E	X	C	-	-	E
Arsenic Acid	E	E	E	E	E	E	E	E	E	E
Asphalt	X	C	F	X	C	X	X	E	E	C
Astm Fuel A	X	C	C	X	E	X	X	-	-	E
Astm Fuel B	X	X	X	X	C	X	X	-	-	C
Astm Fuel C	X	X	X	X	C	X	X	-	-	C
Astm Oil No.1	X	E	C	X	E	X	X	E	E	E
Astm Oil No.2	X	C	X	X	E	X	X	E	E	E
Astm Oil No.3	X	C	C	X	E	X	X	E	E	E
Astm Oil No.4	X	X	X	X	C	X	X	-	-	C
Automatic Trasmission Fluid	X	C	C	X	E	X	X	-	-	E
Banana Oil	C	X	C	C	X	X	-	-	-	X
Barium Chloride	E	E	E	E	E	E	E	E	E	E
Barium Hydroxide	E	E	E	E	E	E	E	E	E	E
Barium Sulphide	E	E	E	E	E	E	G	E	E	E
Beer	E	E	E	E	E	E	E	E	E	E
Beet Sugar Liquors	E	C	E	E	E	E	E	E	E	E
Benzal Chloride	G	-	-	-	X	-	-	-	-	X
Benzaldehyde	G	X	X	E	X	X	X	E	E	X
Benzene	X	C	C	C	X	X	X	E	F	X
Benzene Carboxylic Acid	E	E	C	C	X	X	-	-	-	X
Benzine (Gasoline)	X	C	C	X	E	-	X	E	E	E
Benzoic Acid	C	E	C	C	X	X	X	-	-	X
Benzol (Benzene)	X	C	C	C	X	X	X	E	F	X
Benzotrichloride	-	X	X	E	X	X	-	-	-	X
Benzyl Acetate	E	E	G	E	X	X	-	-	-	X
Benzyl Alcohol	E	C	C	C	X	X	X	-	-	X
Benzyl Chloride	X	X	X	X	X	X	X	-	-	X
Benzyl Ether (Dibenzyl Ether)	G	X	X	C	X	X	X	-	-	X
Biodiesel (bd100 o b100)	-	-	-	-	-	-	-	-	-	E
Biodiesel (bd20 o b20)	-	-	-	-	-	-	-	-	-	E
Bioethanol (e85)	-	-	-	-	-	-	-	-	-	E
Bis (2-cloroethyl) ether	-	-	-	-	-	-	-	-	-	-
Black sulfate liquor	G	G	G	G	G	G	G	E	E	G
Bleach	E	C	E	E	X	C	X	G	F	X
Borax Solution	E	E	E	E	C	C	G	E	E	C
Boric Acid	E	E	E	E	E	E	E	E	E	E
Brake Fluid (hd-557)12 days	E	C	C	E	C	X	E	-	-	C
Brine	E	E	E	E	E	E	-	E	E	E
Bromacil	-	-	-	-	-	-	-	-	-	-
Bromobenzene	X	X	X	X	X	X	X	-	-	X
Bromochlorometane	C	X	X	G	X	X	-	F	F	X
Bromoethane (Ethyl Bromide)	C	X	X	X	C	C	X	E	E	C
Bromotoluene	X	-	X	-	X	X	-	-	-	X
Bugdioxane	-	-	-	-	-	-	-	-	-	-
Bunker oil	X	G	C	X	E	X	X	-	-	E
Butadiene	X	X	G	X	X	X	X	E	E	X
Butane	X	E	C	X	E	X	X	E	E	E
Butanoic Acid	X	X	C	C	C	C	-	-	-	C
Butanol (Butyl Alcohol)	C	E	E	C	E	E	E	E	E	E
Butanone	E	X	X	E	X	X	X	E	E	X

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.

KEY TO CHEMICAL RESISTANT CHART

(all data based on +68°F (+20°C) unless noted)

E Excellent
 G Good
 F Fair
 C Conditional
 I Insufficient Data
 X Not Recommended
 No Data

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Butoxyethanol	C	X	G	E	C	X	-	-	-	C
Butyl Acetate	C	X	X	C	X	X	X	E	E	X
Butyl Acrylate	X	X	X	C	X	X	X	E	E	X
Butyl Alcohol	C	E	E	C	E	E	E	E	E	E
Butyl Aldehyde (Butyraldehyde)	C	X	X	C	X	X	X	E	E	X
Butyl Benzyl Phthalate	E	E	X	E	X	X	-	E	E	X
Butyl Carbitol	E	X	C	E	X	X	X	-	-	X
Butyl Cellosolve	C	X	G	C	C	X	X	E	E	C
Butyl chloride	F	X	X	X	X	X	-	-	-	X
Butyl Ether	C	C	X	C	X	X	X	E	E	X
Butyl Ether Acetaldehyde	G	X	X	X	X	X	-	-	-	X
Butyl Ethyl Ether	X	X	C	F	G	X	-	-	-	G
Butyl Oleate	C	X	X	C	X	X	X	-	-	X
Butyl Phthalate	G	X	X	E	X	X	X	E	E	X
Butyl Stearate	C	X	X	X	C	X	X	E	E	C
Butylene	X	C	C	X	C	X	X	-	-	C
Butyraldehyde	C	X	X	C	X	X	X	E	E	X
Butyric Acid	X	X	C	C	C	C	X	E	E	C
Butyric Anhydride	F	G	G	E	C	F	-	-	-	C
Cadmium Acetate	E	-	E	-	X	X	-	-	-	X
Calcium Aluminate	E	-	E	-	E	E	-	-	-	E
Calcium Bichromate	E	E	F	E	C	-	-	-	-	C
Calcium Bisulfide	X	E	F	E	C	X	G	-	-	C
Calcium Chloride	E	E	E	E	E	E	E	E	E	E
Calcium Hydroxide	E	E	E	E	E	E	E	E	E	E
Calcium Hypochlorite	E	C	E	E	C	C	X	E	E	C
Calcium Nitrate	E	E	E	E	E	E	E	-	-	E
Calcium Sulfide	E	E	E	E	E	C	X	-	-	E
Calcium Acetate	E	C	C	E	C	E	X	-	-	C
Caprylic Acid	F	-	G	-	F	C	-	-	-	F
Carbamide (Urea)	E	G	E	E	G	E	-	E	E	G
Carbitol	C	C	C	C	C	C	E	E	E	C
Carbolic Acid Phenol	C	-	C	-	-	C	-	-	-	-
Carbon Dioxide	E	G	E	G	E	G	G	E	E	E
Carbon Disulfide (Carbon Bisulfide)	X	X	X	X	X	X	-	C	C	X
Carbon Monoxide	E	C	C	E	E	C	G	E	E	E
Carbon Tetrachloride	X	X	X	X	X	X	-	E	E	X
Carbonic Acid	E	E	E	E	C	E	G	E	E	C
Castor Oil	C	E	E	C	E	E	E	E	E	E
Caustic Soda	E	G	E	G	C	E	E	E	E	C
Cellosolve Acetate	C	X	X	G	X	C	X	E	E	X
Celluguard	E	E	E	E	E	E	E	-	-	E
Cetylic Acid (Palmitic Acid)	C	G	C	C	E	C	G	E	E	E
China Wood Oil (Tung Oil)	C	C	C	X	E	X	X	E	E	E
Chlorinated Solvents	X	X	X	X	X	X	X	E	E	X
Chloro-2-Propanone	C	-	X	-	-	X	-	-	-	-
Chloroacetic Acid	C	X	G	C	X	X	X	E	E	X
Chloroacetone	C	X	X	E	X	X	X	E	E	X
Chlorobenzene	X	X	X	X	X	X	X	E	E	X
Chlorobutane	F	X	X	X	X	X	-	-	-	X
Chlorodane (Chlordane)	X	C	C	X	C	X	X	-	-	C
Chloroethyl Benzene	X	X	X	X	C	X	-	-	-	C
Chloroform	X	X	X	X	X	X	X	F	F	X
Chloropentane	X	X	X	X	X	X	-	-	-	X
Chlorosulfonic Acid	X	X	X	X	X	X	X	F	X	X
Chlorotoluene	X	X	X	X	X	X	X	-	-	X

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Chlorox	C	C	C	G	C	X	X	-	-	C
Chrome Plating Solutions	C	X	X	C	X	X	X	-	-	X
Chromic Acid	C	X	E	C	X	C	X	E	E	X
Chromium Trioxide (Chromic Oxide)	G	X	E	C	X	X	X	-	-	X
Cinnamene (Vinylbenzene)	X	X	X	X	C	X	X	-	-	C
Cis-9-Octadecenoic Acid (Oleic Acid)	X	C	C	C	G	X	X	E	E	G
Citric Acid	E	E	E	E	E	E	E	E	E	E
Coal Tar Oil (Coal Oil)	X	G	F	X	E	X	X	E	E	E
Coal Tar	X	C	C	X	C	X	X	E	E	C
Coal Tar Naphtha	X	X	X	X	X	X	-	E	E	X
Coconut Oil	C	C	C	C	E	X	X	E	E	E
Coke Oven Gas	C	X	C	X	X	C	X	E	E	X
Coolanol (Monsanto)	X	C	C	X	E	X	X	-	-	E
Copper Chloride	E	C	C	E	E	E	E	E	E	E
Copper Cyanide	E	E	E	E	E	E	E	E	E	E
Copper Hydrate	E	-	G	-	G	F	-	-	-	G
Copper Hydroxide (Copper Hydrate)	E	-	G	-	G	F	-	-	-	G
Copper Sulfate	C	E	E	E	E	C	G	E	E	E
Corn Oil	C	C	C	C	E	X	X	E	E	E
cottonseed Oil	C	C	C	C	E	X	X	E	E	E
Creosote	X	C	X	X	C	X	X	E	E	C
Cresols	X	X	X	X	X	X	X	E	E	X
Cresylic Acid	X	X	X	X	X	X	X	E	E	X
Crotonaldehyde	E	X	X	E	X	X	F	E	E	X
Crude Oil	X	C	C	X	C	X	X	E	E	C
Cumene	X	X	X	X	X	X	X	-	-	X
Cupric Carbonate	-	-	-	-	-	-	-	-	-	-
Cupric Hydroxide (Copper Hydroxide)	E	-	G	-	G	F	-	-	-	G
Cupric Nitrate (Copper Nitrate)	E	E	E	C	C	G	-	E	E	C
Cupric Sulfate (Copper Sulfate)	C	E	E	E	E	C	G	E	E	E
Cutting Oil	X	C	C	X	E	C	X	-	-	E
Cyclohexane	X	X	C	X	E	X	X	E	E	E
Cyclohexanol	X	C	C	X	G	C	X	E	E	G
Cyclohexanone	C	X	X	C	X	X	X	E	E	X
Cyclopentane	X	C	X	X	G	X	-	-	-	G
Cyclopentanol	-	-	-	-	-	-	-	-	-	-
Cyclopentanone	X	-	X	-	X	X	-	-	-	X
Cyclopentil alcohol (cyclopentanol)	-	F	-	C	X	-	-	-	-	X
D-Furaldehyde (Furfural)	C	F	C	E	G	X	-	-	-	G
DDT in Kerosene	X	C	C	X	E	X	X	-	-	E
Decahydronaphthalene (Decalin)	X	X	X	X	X	X	E	E	E	X
Decahydroxynaphthalene	-	-	-	-	-	-	-	-	-	-
Decalin	X	X	X	X	X	X	E	E	E	X
Decyl Alcohol (Decanol)	X	X	C	X	E	X	-	-	-	E
Decyl Aldehyde	F	-	X	X	X	X	-	-	-	X
Decyl Butyl Phthalate	E	-	X	-	X	X	-	-	-	X
Decil Carbinol	-	-	-	-	-	-	-	-	-	-
Detergent, Water Solution	E	C	C	E	E	E	G	E	E	E
Developing Fluid (Photo)	C	E	E	C	E	E	G	-	-	E
Dextron	X	C	X	X	E	X	X	-	-	E
Di (2ethylhexyl) Adipate (Diocetyl Adipate)	E	X	X	G	X	X	-	G	G	X
Di (2ethylhexyl) Phthalate (Diocetyl Phthalate)	C	X	X	C	X	X	X	E	E	X
Di-Iso-Butylene	X	C	X	X	C	X	X	E	-	C
Di-Iso-Decyl Phthalate	E	X	X	E	X	X	-	-	-	X

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.

KEY TO CHEMICAL RESISTANT CHART

(all data based on +68°F (+20°C) unless noted)

E Excellent **G** Good **F** Fair **C** Conditional **I** Insufficient Data **X** Not Recommended No Data

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Di-Iso-Propanolamine	E	G	F	E	G	G	-	-	-	G
Di-Iso-Propyl Ether	X	C	C	X	G	X	-	E	E	G
Di-Iso-Propyl Ketone	E	X	X	E	X	X	X	E	-	X
Di-P-Mentha-1,8-Diene (Cinene)	X	X	X	X	C	X	-	-	-	C
Diacetone Alcohol	E	F	C	E	X	X	X	E	E	X
Diacetyl methane (Acetylacetone)	E	X	X	E	X	-	X	-	-	X
Diallylphthalate (Diallyl Phthalate)	-	-	-	-	-	-	-	-	-	-
Diammonium Orthophosphate	-	E	-	E	E	-	-	-	-	E
Diamyl Naphthalene	E	-	X	-	-	X	-	E	E	-
Diamylamine	E	C	C	E	G	G	X	-	-	G
Diamylene	X	X	X	X	-	X	-	-	-	-
Diamylphenol	X	-	X	-	X	X	-	E	E	X
Dibenzyl Ether	C	X	X	C	X	X	X	-	-	X
Dibromobenzene	X	X	X	X	X	X	-	-	-	X
Dibromomethane (Methylene Bromide)	X	X	X	C	X	X	-	-	-	X
Dibutyl Ether	C	C	X	C	X	X	X	E	E	X
Dibutyl Phthalate	C	X	X	C	X	X	X	E	E	X
Dibutyl Sebacate	C	X	X	C	X	X	X	E	E	X
Dibutylamine	X	C	C	F	X	X	X	-	-	X
Dicalcium Phosphate	E	E	E	E	E	E	-	-	-	E
Dichloroethylene (1,2-Dichloroethene)	C	X	X	C	X	X	-	F	F	X
Dichloroacetic Acid	C	X	X	X	X	X	X	E	E	X
Dichlorobenzene	X	X	X	X	X	X	X	-	-	X
Dichlorobutane	X	X	X	X	C	X	X	-	-	C
Dichlorodifluoromethane	C	C	C	C	C	C	E	E	G	C
Dichloroethane	C	X	X	X	X	X	X	E	E	X
Dichloroethyl ether	X	X	X	X	X	X	-	-	-	X
Dichlorohexane	X	X	X	X	X	X	-	-	-	X
Dichloromethane	X	X	X	X	X	X	X	-	-	X
Dichloropentane	X	X	X	X	X	X	X	-	-	X
Dichloropropane	X	X	X	X	F	X	-	G	G	F
Dichloropropene	X	X	X	X	C	X	-	G	G	C
Dichlorotoluene	-	-	-	-	-	-	-	-	-	-
Diesel Oil	X	C	C	X	E	X	X	E	E	E
Diethanol Amine	E	G	F	G	C	G	X	-	-	C
Diethylbenzene	X	-	X	-	-	X	X	-	-	-
Diethyl Ether	X	X	X	X	X	X	X	E	E	X
Diethyl Ketone	G	X	X	G	X	X	-	E	E	X
Diethyl Oxalate	X	X	X	X	X	F	-	-	-	X
Diethyl Phthalate	X	X	X	F	X	X	-	E	E	X
Diethyl Sebacate	G	X	F	F	C	X	X	-	-	C
Diethyl Sulfate	C	E	X	E	X	X	E	-	-	X
Diethyl Amine	C	C	C	C	C	C	G	E	E	C
Diethylene Glycol	E	E	E	E	E	E	E	E	E	E
Diethylene Oxide	X	X	X	E	X	X	-	-	-	X
Diethylenetriamine	E	X	F	E	G	G	X	-	-	G
Diethyltriamine	-	-	-	-	-	-	-	-	-	-
Dihydroxy Succinic Acid	G	G	E	G	G	E	-	-	-	G
Dihydroxydiethyl Ether (Diethylene Glycol)	E	E	E	E	E	E	-	E	E	E
Diisobutyl Ketone	G	X	X	E	X	X	X	E	E	X
Diisodecyl Phthalate	E	X	X	E	X	X	-	E	E	X
Diisooctyl Adipate	E	X	X	E	X	X	-	-	-	X
Diisooctyl Phthalate	E	X	X	G	X	X	-	E	E	X
Dimethyl Carbinol	E	G	E	E	C	E	-	E	E	C
Dimethyl Ketone	E	C	X	E	X	C	F	E	E	X

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Dimethyl Phthalate	C	X	X	C	X	X	X	E	E	X
Dimethyl Sulfate	G	X	X	X	X	X	-	E	E	X
Dimethyl Sulfide	F	X	X	X	X	X	-	-	-	X
Dimethyl-3-Pentanone	-	-	-	-	-	-	-	-	-	-
Dimethyl-4-Heptanone	-	-	-	-	-	-	-	-	-	-
Dimethylamine	G	X	X	E	F	G	X	E	E	F
Dimethylaniline	G	X	X	E	X	X	X	-	-	X
Dimethylbenzene	X	X	X	X	X	X	X	-	-	X
Dimethylbutane (Iso-Pentane)	X	-	X	-	-	X	-	-	-	-
Diethyl adipate	E	X	X	G	X	X	-	-	-	X
Diethyl phthalate	C	X	X	C	X	X	X	E	E	X
Dioxalane	-	-	-	-	-	-	X	-	-	-
Dioxane	C	X	X	C	X	X	X	E	E	X
Dipentene	X	X	X	X	C	X	X	-	-	C
Dipentylamine (Diamylamine)	E	C	C	E	G	G	X	-	-	G
Dipropylamineolamine	-	-	-	-	-	-	-	-	-	-
Dipropylene glycol	E	E	E	E	E	E	-	-	-	E
Disodium phosphate	E	E	E	E	E	E	-	-	-	E
Divinyl benzene	X	X	X	X	X	X	X	-	-	X
Dowell inhibitor	-	-	-	-	-	-	-	-	-	-
Dowfax 2a1 Solvent	-	-	-	-	-	-	-	-	-	-
Dowfax 2a1 Ta	-	-	-	-	-	-	-	-	-	-
Dowfax 6a1 Solvent	-	-	-	-	-	-	-	-	-	-
Dowfax 6a1 Ta	-	-	-	-	-	-	-	-	-	-
Dowthermn, A and E	X	X	C	X	X	X	X	-	-	X
Dry Cleaning Fluids	X	X	X	X	C	X	X	-	-	C
Ducgkirioebaane	-	-	-	-	-	-	-	-	-	-
Durd Aw-16,31	-	-	-	-	-	-	-	-	-	-
Duro Fr-Hd	-	-	-	-	-	-	-	-	-	-
Ethanoic Acid (Acetic Acid)	-	C	-	C	C	-	G	E	E	C
Ethanol (Grain Alcohol)	E	E	E	E	C	E	E	E	E	E
Ethanolamine	C	C	C	E	C	C	X	-	-	C
Ethers	X	X	X	X	F	X	X	E	E	F
Ethyl Acetate	C	X	X	C	X	X	X	E	E	X
Ethyl Acetoacetate	C	X	X	C	X	C	F	-	-	X
Ethyl Acetone (2-Pentanone)	G	X	X	G	X	X	-	-	-	X
Ethyl Acrylate	C	X	X	C	X	X	X	-	-	X
Ethyl Alcohol	E	E	E	E	C	E	E	E	E	E
Ethyl Aldehyde	E	X	F	E	X	C	-	E	E	X
Ethyl Aluminium Dichloride	X	-	X	-	X	X	-	-	-	X
Ethyl Benzene	X	X	X	X	X	X	X	E	E	X
Ethyl Bromide	X	X	X	X	C	C	X	E	E	C
Ethyl Butyl Acetate	E	-	G	-	X	X	-	-	-	X
Ethyl Butyl Alcohol (Ethylbutanol)	E	-	E	-	-	E	-	-	-	-
Ethyl Cellulose	C	C	C	C	C	C	G	E	E	C
Ethyl Chloride	E	X	C	C	E	C	G	E	E	E
Ethyl Dichloride	F	X	X	X	X	X	X	E	E	X
Ethyl Diisobutylthio-Cabarmate	-	-	-	-	-	-	-	-	-	-
Ethyl Ether	X	X	X	X	X	X	X	E	E	X
Ethyl Formate	C	C	C	C	X	X	X	-	-	X
Ethyl Iodide	F	X	X	F	X	X	-	E	E	X
Ethyl Oxalate	X	X	X	E	X	E	X	-	-	X
Ethyl Phthalate	X	X	X	F	X	X	-	E	E	X
Ethyl Silicate	E	E	C	E	E	C	G	-	-	E
Ethyl-N-Butyl Ketone	G	X	X	G	X	X	-	-	-	X
Ethyl-1-Butanol	E	E	E	E	E	E	-	-	-	E

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.

KEY TO CHEMICAL RESISTANT CHART

(all data based on +68°F (+20°C) unless noted)

E Excellent
 G Good
 F Fair
 C Conditional
 I Insufficient Data
 X Not Recommended
 No Data

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Ethylamine	C	C	F	E	C	C	X	-	-	C
Ethylene Chlorohydrin	C	C	C	C	X	C	G	-	-	X
Ethylene Diamine	E	E	C	E	C	C	G	E	E	C
Ethylene Dibromide	C	X	X	C	X	X	X	F	F	X
Ethylene Dichloride	C	X	X	X	X	X	X	F	F	X
Ethylene Glycol Monoethyl Acetate	-	-	-	-	-	-	-	-	-	-
Ethylene Glycol Monobutyl Ether	E	X	C	E	F	X	X	E	E	F
Ethylene Glycol Monoethyl Ether (Ethoxyethanol)	C	X	X	C	C	X	-	E	E	C
Ethylene Glycol Monoethyl Ether	-	-	-	-	-	-	-	-	-	-
Ethylene Glycol	E	E	E	E	E	E	E	E	E	E
Ethylene Oxide	C	X	X	C	X	X	X	E	E	X
Fatty Acids	C	C	C	X	C	X	X	E	G	C
Ferric Bromide	E	-	E	-	E	E	-	-	-	E
Ferric Chloride	E	C	C	E	E	E	E	-	E	E
Ferric Nitrate	E	E	E	E	E	E	E	-	E	E
Ferric Sulfate	E	E	E	E	E	E	E	-	E	E
Ferrous Acetate	E	X	E	G	X	X	-	-	-	X
Ferrous Chloride	E	E	E	E	E	E	-	-	E	E
Ferrous Sulfate	E	E	E	E	E	E	E	-	E	E
Fluoroboric Acid	C	E	E	E	E	E	E	E	E	E
Fluorine	X	X	X	E	X	X	-	G	G	X
Fluorosilicic Acid	E	E	E	E	E	E	G	E	E	E
Formaldehyde	C	C	C	C	C	C	G	E	E	C
Formalin (Formaldehyde)	C	G	C	E	G	C	G	E	E	G
Formic acid	E	C	E	E	C	C	E	E	E	C
Freon so2	-	-	-	-	-	-	-	-	-	-
Freon 113	X	E	C	X	E	C	G	-	-	E
Freon 12	X	C	E	C	C	X	E	F	G	C
Freon 22	C	E	E	C	X	C	E	F	E	X
Fuel A (Astm)	X	C	C	X	E	X	-	-	-	E
Fuel B (aAstm)	X	X	X	X	C	X	-	-	-	C
Fuel Oil	X	C	C	X	E	X	X	E	E	E
Furan (Furfuran)	X	X	X	X	X	X	X	E	E	X
Furfural	C	X	C	C	X	X	X	E	E	X
Furfuran (Furan)	X	X	X	X	X	X	X	E	E	X
Furfuryl Alcohol	C	X	X	C	X	X	X	E	E	X
Gallic Acid	C	C	C	C	C	E	G	E	E	C
Gallotannic Acid	G	E	E	E	-	E	-	-	-	-
Gas, Coal	-	-	-	-	-	-	-	-	-	-
Gas, High Octane	-	-	-	-	-	-	-	-	-	-
Gasoline	C	X	C	X	E	C	X	E	E	E
Glacial Acrylic Acid (Acrylic Acid)	X	X	G	X	X	X	-	-	-	X
Gluconic acid	F	E	G	E	C	X	-	-	-	C
Glucose	E	C	E	E	E	E	E	E	E	E
Glycerine	E	E	E	E	E	E	E	E	E	E
Glycerol	E	E	E	E	E	E	E	E	E	E
Glycogenic Acid (Gluconic Acid)	F	E	G	E	F	X	-	-	-	F
Glycols	E	E	E	E	E	E	E	E	E	E
Glyconic Acid (Gluconic Acid)	F	E	G	E	F	X	-	-	-	F
Glycyl Alcohol	-	-	-	-	-	-	-	-	-	-
Grease	X	F	C	X	E	X	X	-	-	E
Green Sulphate Liquor	E	C	G	E	C	C	G	-	-	C
Halon 1211	-	-	-	-	-	-	-	-	-	-
Helium	E	E	E	E	E	E	E	-	-	E
Heptaldehyde	C	C	X	C	E	X	X	-	-	E

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Heptanal	C	C	X	C	E	X	X	-	-	E
Heptane	X	C	C	X	E	X	X	-	E	E
Heptane Carboxylic Acid	-	-	-	-	-	-	-	-	-	-
Heptanoic Acid	X	C	C	X	E	X	-	-	-	E
Heptanone	-	-	-	-	-	-	-	-	-	-
Hexadecanoic Acid	G	X	X	G	E	E	G	E	E	E
Hexaldehyde	C	C	C	C	X	X	X	E	E	X
Hexane	X	C	C	X	E	X	X	E	E	E
Hexanol	C	C	C	C	C	E	E	E	E	C
Hexene	X	C	C	X	C	X	X	-	-	C
Hexyl Alcohol	C	C	C	C	C	E	E	E	E	C
Hexyl Methyl Ketone (Methyl Hexyl Ketone)	G	C	X	G	X	X	-	-	-	X
Hexylamine	G	G	F	G	F	F	-	-	-	F
Hexylene Glycol	E	E	E	F	C	E	-	-	-	C
Histowax (Paraffin Wax)	X	-	C	-	-	X	-	-	-	-
Hydraulic & Motor Oil	C	C	C	C	C	X	X	E	E	C
Hydrazine	C	C	C	E	C	C	G	-	-	C
Hydrobromic Acid	E	C	E	E	X	E	X	E	E	X
Hydrochloric Acid	C	C	C	C	C	C	X	C	C	C
Hydrocyanic Acid	C	C	E	E	C	C	G	-	-	C
hHdrofluoric Acid	C	C	E	C	C	C	X	E	E	C
Hydrofluosilicic Acid	E	C	E	E	X	E	G	E	E	X
Hydrogen Chloride Anhydrous	E	C	E	E	X	X	X	-	-	X
Hydrogen Dioxide (10%) (Hydrogen Peroxide)	G	F	C	G	F	G	-	-	-	F
Hydrogen Gas	E	E	E	E	E	C	G	E	E	E
Hydrogen Peroxide over 10%	C	X	C	C	X	C	X	C	F	X
Hydrogen Peroxide 10%	G	F	C	G	F	G	X	E	E	F
Hydrogen Sulfide (Wet)	E	E	G	E	X	X	X	E	E	X
Hydroxy Benzene (Phenol)	C	X	C	C	X	C	-	-	-	X
Hydroxyisobutyronirile (Acetone Cyanohydrin)	E	G	F	E	C	C	-	-	-	C
Hydroxytoluene (Benzyl Alcohol)	C	C	C	C	X	X	X	-	-	X
Hyvar Vxl	-	-	-	-	-	-	-	-	-	-
Iminodi-2-Propanol (Diisopropanolamine)	E	G	F	E	G	G	-	-	-	G
Iminodiethanol (Diethanolamine)	C	G	F	G	C	C	X	-	-	C
Iodine	C	C	C	C	C	X	G	E	E	C
Iodine pentafluoride	X	X	X	X	X	X	X	-	-	X
Iodoform	X	X	X	E	E	X	-	-	-	E
Iso-Butanal (Isobutyraldehyde)	-	F	-	G	X	X	G	E	E	X
Iso-Butylamine	E	X	F	G	X	F	-	-	-	X
Iso-Butylbromide	X	X	X	X	X	X	-	-	-	X
Iso-Butylcarbinol (Isoamyl Alcohol)	E	E	E	E	E	X	-	-	-	E
Isocyanates	G	X	F	G	C	F	-	E	E	C
Isooctane	X	C	C	X	E	X	X	E	E	E
Isopropyl acetate	C	X	X	C	X	X	X	E	E	X
Isopropyl alcohol	E	C	E	E	C	E	E	E	E	C
Isopropyl ether	X	X	C	X	G	X	X	E	E	G
Jet Fuels	X	C	X	X	C	X	X	E	E	C
Jp-4 Oil	X	X	X	X	E	X	X	-	-	E
Kerosene	X	C	C	X	E	X	X	E	E	E
Ketones	G	C	C	E	C	C	E	E	E	C
Lacquer Solvents	X	X	X	X	X	X	-	E	E	X
Lactic Acid - Cold	E	C	E	C	C	E	G	G	G	C

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.

KEY TO CHEMICAL RESISTANT CHART

(all data based on +68°F (+20°C) unless noted)

E Excellent G Good F Fair C Conditional I Insufficient Data X Not Recommended No Data

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Lactic Acid - Hot	E	C	E	C	C	E	X	G	G	C
Lard	C	C	C	C	E	X	X	E	E	E
Lavender Oil	X	X	X	X	C	X	X	-	-	C
Lead Acetate	E	C	X	E	C	E	X	E	E	C
Lead Nitrate	E	E	E	E	E	E	E	-	-	E
Lead Sulfate	E	E	E	E	E	E	-	E	E	E
Lime	E	G	G	E	G	E	-	E	E	G
Lime Bleach (Calcium Hypochlorite)	E	C	E	E	C	C	E	-	-	C
Lime Sulfur	E	E	E	E	E	C	X	E	E	E
Limonene (Dipentene)	X	X	X	X	C	X	-	-	-	C
Linoleic Acid	X	C	X	X	C	X	X	-	-	C
Linseed Oil	C	C	C	C	E	X	X	E	E	E
Liquid Petroleum Gas (Lpg)	X	G	C	X	E	X	X	E	E	E
Lubricating Oil	X	C	C	X	C	X	X	E	E	C
Lye Solutions (Caustic Soda Solution)	E	G	E	G	C	E	G	-	-	C
Mek	E	X	X	E	X	X	X	E	E	X
Magnesium Acetate	E	X	E	G	X	X	X	-	-	X
Magnesium Chloride	E	E	E	E	E	E	E	E	E	E
Magnesium Hydrate (Magnesium Hydroxide)	E	C	E	E	C	C	G	E	E	C
Magnesium Hydroxyde	E	C	E	E	C	C	G	E	E	C
Magnesium Sulfate	E	E	E	E	E	C	G	E	E	E
Maleic Acid	X	X	X	C	X	X	X	E	E	X
Maleic Anhydride	C	X	X	C	X	X	X	-	-	X
Malic Acid	X	C	C	C	E	E	G	C	C	E
Manganous Sulfate	G	E	E	E	E	G	-	-	-	E
Mapp	-	-	-	-	-	-	-	-	-	-
Mercury	E	E	E	E	E	E	E	E	E	E
Mercury Vapors	E	G	E	E	E	G	E	-	-	E
Mesityl Oxide	F	X	X	C	X	X	X	-	-	X
Methallyl Alcohol	E	E	E	E	E	E	-	-	-	E
Methallyl Chloride	X	X	X	-	-	X	-	-	-	-
Methane Carboxylic Acid *see Acetic Acid	-	-	-	-	-	-	-	E	E	-
Methanoic Acid (Formic Acid)	E	E	E	E	G	C	E	E	E	G
Methanol (Methyl Alcohol)	C	E	E	E	C	E	E	E	E	C
Methanol (Wood Alcohol)	C	E	E	E	C	E	E	E	E	C
Methoxy Ethanol	E	E	E	E	C	E	-	E	E	C
Methoxyethoxy Ethanol	-	-	-	-	-	-	-	-	-	-
Methoxypropenyl Benzene	-	-	-	-	-	-	-	-	-	-
Methyl Acetate	C	C	X	C	X	C	X	-	-	X
Methyl Acetoacetate	C	X	X	C	X	X	X	-	-	X
Methyl Acetone (Ethyl Methyl Ketone)	E	X	X	E	X	X	X	E	E	X
Methyl Acetylene Propadiene	-	-	-	-	-	-	-	-	-	-
Methyl Allyl Alcohol	-	-	-	-	-	-	-	-	-	-
Methyl Allyl Chloride (Methylallyl Chloride)	X	X	X	-	-	X	-	-	-	-
Methyl Amyl Carbinol (S-Heptyl Alcohol)	G	G	E	E	E	G	-	-	-	E
Methyl Benzene (Toluene)	X	X	X	X	X	X	X	F	F	X
Methyl Bromide	C	X	X	X	C	X	X	F	F	C
Methyl Butane (Iso-Pentane)	X	X	X	X	E	X	-	-	-	E
Methyl Butyl Alcohol	-	-	-	-	-	-	-	-	-	-
Methyl Butyl Ketone	E	X	X	E	X	X	X	E	E	X
Methyl Carbitol (Diethylene Glycol Monomethyl Ether)	-	F	-	G	F	-	-	-	-	F

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Methyl Cellosolve	C	C	C	C	C	X	X	E	E	C
Methyl Chloride	C	X	X	C	X	X	X	F	F	X
Methyl Cyanide	E	E	G	E	C	G	-	-	-	C
Methyl Ethyl Ketone	E	X	X	E	X	X	X	E	E	X
Methyl Hexanol	E	E	E	E	E	E	-	-	-	E
Methyl Methacrilate	X	X	X	X	X	X	X	E	E	X
Methyl Normal Amyl Ketone	-	E	X	E	C	X	-	-	-	C
Methyl Propyl Ether	X	X	C	X	X	X	-	-	-	X
Methyl Salicylate	C	X	X	C	X	X	-	E	E	X
Methyl Styrene (P-vNyltoluene)	X	X	X	X	X	X	-	-	-	X
Methyl Sulfide (Dimethyl Sulfide)	F	X	X	X	X	X	-	-	-	X
Methyl Tertiary Metyl Ether	-	-	-	-	-	-	-	-	-	-
Methyl 1-2, 4-Pentanediol	-	-	-	-	-	-	-	-	-	-
Methyl-Iso-Amyl-Ketone	G	-	X	-	-	X	-	-	-	-
Methyl-I-Propanol	-	-	-	-	-	-	-	-	-	-
Methyl-2-Butanol	-	-	-	-	-	-	-	-	-	-
Methyl-2-Butanone (Methyl Isopropyl Ketone)	C	X	X	C	X	X	X	-	-	X
Methyl-2-Hexanone (Methyl Isoamyl Ketone)	G	-	X	-	-	X	-	-	-	-
Methyl-2-Pentanol (Methyl Amyl Alcohol)	E	G	E	E	G	G	-	-	-	G
Methyl-2-Pentanone (Methyl ilobutyl Ketone)	C	X	X	C	X	X	-	-	-	X
Methyl-2-Propen-I-OL	-	-	-	-	-	-	-	-	-	-
Methyl-3-Penten-1-One	-	-	-	-	-	-	-	-	-	-
Methyl-4-Isopropyl Benzene (Cymene)	X	X	X	X	X	X	-	-	-	X
Methyl Amyl Acetate	-	-	X	-	-	X	-	-	-	-
Methyl Amyl Alcohol	E	G	E	E	G	G	-	-	-	G
Methylcyclohexane	X	X	C	X	X	X	-	-	-	X
Methylene Bromide	X	X	X	X	C	X	-	E	E	C
Methylene Chloride	X	X	X	C	X	X	X	F	F	X
Methylethyl Ketone	E	X	X	E	X	X	X	-	-	X
Methyl Hexyl Ketone	G	C	X	G	X	X	-	E	-	X
Methyl Isobutyl Carbinol (Methyl Amyl Alcohol)	E	X	E	C	X	G	-	-	-	X
Methylisobutyl Ketone	C	X	X	C	X	X	X	E	E	X
Methylisopropyl Ketone	C	X	X	C	X	X	X	-	-	X
Methylactonitrile (Acetone Cyanohydrin)	E	G	F	E	X	F	-	-	-	X
M-Ethylphenol	-	-	-	-	-	-	-	-	-	-
Methylpropyl Carbinol	E	-	E	-	E	E	-	-	-	E
Methylpropyl Ketone	G	X	X	G	X	X	-	E	E	X
Mil-A-6091	E	E	E	E	C	E	-	-	-	C
Mil-C-4339	X	X	X	X	E	X	-	-	-	E
Mil-C-7024	X	C	X	X	E	X	-	-	-	E
Mil-E-9500	E	E	E	E	E	E	E	-	-	E
Mil-F-16884	X	C	C	X	E	X	X	-	-	E
Mil-ff17111	X	C	X	X	E	X	X	-	-	E
Mil-F-25558 (RJ-1)	X	C	C	X	E	X	X	-	-	E
Mil-G-10924	X	C	C	X	E	X	X	-	-	E
Mil-G-25013	X	C	C	E	E	C	X	-	-	E
Mil-G-25537	X	C	C	X	E	X	X	-	-	E
Mil-G-3545	X	C	C	X	E	X	-	-	-	E
Mil-G-5572	X	X	X	X	E	X	X	-	-	E
Mil-G-7711	X	X	X	X	E	X	X	-	-	E

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.

KEY TO CHEMICAL RESISTANT CHART

(all data based on +68°F (+20°C) unless noted)

E Excellent
 G Good
 F Fair
 C Conditional
 I Insufficient Data
 X Not Recommended
 No Data

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Mil-H-05606 (HFA)	X	C	C	C	E	X	-	-	-	E
Mil-H-13910	G	E	G	E	E	E	E	-	-	E
Mil-H-19457	E	X	X	C	X	X	X	-	-	X
Mil-H-22251	E	C	C	E	C	-	G	-	-	C
Mil-H-27601	X	C	C	X	G	X	-	-	-	G
Mil-H-5606 (J43)	X	C	C	C	E	X	-	-	-	E
Mil-H-6083	X	E	C	X	E	C	X	-	-	E
Mil-H-8446 (MLO-8515)	X	E	C	X	G	X	X	-	-	G
Mil-J5161	X	X	X	X	C	X	X	-	-	C
Mil-J-5624 (JP-3,JP-4,JP-5)	X	X	X	X	E	X	X	-	-	E
Mil-L-15016	X	-	C	-	-	X	X	-	-	-
Mil-L-17331	X	-	G	-	-	X	X	-	-	-
Mil-L-2104	X	C	C	X	E	X	-	-	-	E
Mil-L-21260	X	C	C	X	E	X	X	-	-	E
Mil-L-23699	X	C	C	X	C	X	X	-	-	C
Mil-L-25681	E	C	C	E	C	C	G	-	-	C
Mil-L-3150	X	C	C	X	E	X	X	-	-	E
Mil-L-4343	-	-	-	-	-	-	X	-	-	-
Mil-L-6082	-	-	-	-	-	-	X	-	-	-
Mil-L-6085	X	X	X	X	C	X	X	-	-	C
Mil-L-7808	X	X	X	X	G	X	X	-	-	G
Mil-L-7870	X	C	X	X	E	X	X	-	-	E
Mil-L-9000	X	C	C	X	E	X	X	-	-	E
Mil-L-9236	X	X	X	X	C	X	X	-	-	C
Mil-P-27402	E	C	C	E	C	-	G	-	-	C
Mil-R-25567 (RP-1)	-	-	-	-	-	-	-	-	-	-
Mil-R-25576 (RP-1)	X	-	C	-	-	X	-	-	-	-
Mil-S-3136 Type 1 Fuel	X	C	C	X	E	X	X	-	-	E
Mil-S-3136 Type 2 Fuel	X	X	X	X	C	X	X	-	-	C
Mil-S-3136 Type 3 Fuel	X	X	X	X	G	X	X	-	-	G
Mil-S-3136 Type 4 Oil, Lowswell	X	X	C	X	E	X	X	-	-	E
Mil-S-3136 Type 5 Iil, Medswell	X	G	G	X	E	X	X	-	-	E
Mil-S-3136 Type 6 Oil, Hi Swell	X	X	C	X	E	X	X	-	-	E
Mil-S-81087	E	E	E	E	E	E	E	-	-	E
Mineral Oil	C	C	C	X	E	X	X	E	E	E
Mineral Spirits	X	C	G	X	C	X	X	-	-	C
Mobile Hf A	X	C	X	X	E	X	X	-	-	E
Molten Sulfur	G	E	E	E	G	G	-	-	-	G
Mono-Chloroacetic Acid	G	C	G	G	X	C	X	E	E	X
Monobutyl Ether	C	C	C	C	G	X	X	-	-	G
Monochlorobenzene	X	X	X	X	X	X	X	F	F	X
Monochlorodifluoromethane (Chlorodifluoromethane)	C	C	E	C	X	C	E	E	E	X
Monoethanol Amine	C	G	C	C	G	C	G	-	-	G
Monoethyl Amine	C	C	F	E	C	C	F	-	-	C
Morpholine	C	X	X	C	X	X	-	-	-	X
Motor Oil, 40w	X	C	C	X	E	X	-	-	-	E
Mtbe (Methyl Tert-Butyl Ether)	G	X	-	-	X	-	-	-	-	X
Muriatic Acid (Hydrogen Chloride)	C	C	C	F	C	C	X	-	-	C
N-Butanal (Butyraldehyde)	C	X	X	C	X	X	X	E	E	X
N-Butylamine	C	X	X	C	C	X	X	-	-	C
N-Butylbenzene	X	X	X	X	X	X	-	-	-	X
N-Butylbromide	X	X	X	X	X	X	-	-	-	X
N-Butylbutyrate	E	X	X	E	X	X	X	-	-	X
N-Butylcarbinol (Pentyl Alcohol)	E	E	E	E	E	E	-	E	E	E
N-Nonyl Alcohol	E	E	E	E	E	E	-	-	-	E

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
N-Octane	X	G	X	X	C	X	X	E	E	C
N-Serv (75% Xylene)	-	-	-	-	-	-	-	-	-	-
Na-K	-	-	-	-	-	-	-	-	-	-
Naphtha	X	X	C	X	C	X	X	E	E	C
Naphthalene	X	X	X	X	X	X	X	E	E	X
Naphthenic Acid	X	X	X	X	C	X	X	-	-	C
Natural Gas	X	E	E	X	E	C	F	E	E	E
Neohexane	X	G	X	X	E	X	-	-	-	E
Neon Gas	E	E	E	E	E	E	E	-	-	E
Neu-Tri	X	-	X	-	X	X	-	-	-	X
Nickel Acetate	E	G	X	E	C	E	X	-	-	C
Nickel Chloride	E	C	E	E	E	E	E	E	E	E
Nickel Nitrate	E	E	E	E	E	E	-	E	E	E
Nickel Sulfate	E	E	E	E	E	C	G	E	E	E
Nietylene	-	-	-	-	-	-	-	-	-	-
Nitric Acid, Conc (16n)	X	X	X	X	X	X	-	-	-	X
Nitric Acid, Red Fuming	X	X	X	X	X	X	X	X	X	X
Nitric Acid, 10%	E	G	E	E	X	X	X	E	E	X
Nitric Acid, 13n	-	X	-	-	X	X	-	-	-	X
Nitric Acid, 13n +5%	-	X	-	-	X	X	-	-	-	X
Nitric Acid, 20%	G	X	E	E	X	X	X	E	E	X
Nitric Acid, 30%	F	X	E	F	X	X	X	G	G	X
Nitric Acid, 30% - 70%	F	X	C	X	X	X	X	F	F	X
Nitrioltriethanol (Triethanolamine)	E	C	C	E	F	C	G	E	E	F
Nitrobenzene	F	X	X	C	X	X	X	E	E	X
Nitroethane	G	C	G	C	X	G	G	-	-	X
Nitrogen	E	E	E	E	E	E	E	E	E	E
Nitromethane	G	C	C	C	X	G	C	-	-	X
Nitrous Oxide Gas	-	G	-	E	E	-	-	-	-	E
Nonanoic Acid	E	-	X	-	E	X	-	E	E	E
Nonanol (Nonyl Alcohol)	E	E	E	E	E	E	-	-	-	E
Nuto H	-	-	-	-	-	-	-	-	-	-
Nyvac Light	-	-	-	-	-	-	-	-	-	-
Octanoic Acid (N-Caprylic Acid)	F	-	G	-	F	F	-	-	-	F
Octanol (Octyl Alcohol)	C	C	C	C	C	C	E	-	-	C
Octyl Acetate	E	C	E	G	C	C	X	E	E	C
Octyl Alcohol	C	C	C	C	C	C	E	-	-	C
Octyl Aldehyde	F	-	X	-	X	X	-	E	E	X
Octyl Amine	E	G	F	G	F	F	-	-	-	F
Octyl Carbinol	E	E	E	E	E	E	-	-	-	E
Octylene Glycol	E	E	E	E	E	E	-	-	-	E
Oil-Petroleum	-	-	-	-	-	-	X	G	G	-
Oleic Acid	X	F	C	X	G	X	X	E	E	G
Oleum (Fuming Sulfuric Acid)	X	X	X	X	X	X	X	X	X	X
Olive Oil	C	G	C	G	E	X	X	-	-	E
Ortho-Dichlorobenzene	X	X	X	X	X	X	X	-	-	X
Ortho-Dichlorobenzol (O-Dichlorobenzene)	X	X	X	X	X	X	X	-	-	X
Orthoxylene	X	X	X	X	X	X	X	-	-	X
Oxalic Acid	E	G	E	E	G	C	G	E	E	G
Oxydiethanol	-	-	-	-	-	-	-	-	-	-
Ozone	G	F	G	E	X	X	X	E	E	X
P-Cymene	X	X	X	X	X	X	-	-	-	X
Paint Thinner	X	X	X	X	X	X	X	-	-	X
Palmitic Acid	C	G	C	C	E	C	G	E	E	E
Papermakers Alum	-	-	-	-	-	-	-	-	-	-

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.

KEY TO CHEMICAL RESISTANT CHART

(all data based on +68°F (+20°C) unless noted)

E Excellent **G** Good **F** Fair **C** Conditional **I** Insufficient Data **X** Not Recommended No Data

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Para-Dichlorobenzene	X	X	X	X	X	X	X	-	-	X
Paraffin Wax	X	G	E	X	E	X	-	-	-	E
Paraldehyde	E	G	X	E	C	F	-	-	-	C
Paraxylene (P-Dimethylbenzene)	X	X	X	X	X	X	-	-	-	X
PCB	-	-	-	-	-	-	-	-	-	-
Pelargonic Alcohol (Nonyl Alcohol)	E	E	E	E	E	E	-	E	E	E
Pentachloroethane	X	X	X	-	X	X	-	-	-	X
Pentadione	-	-	-	-	-	-	-	-	-	-
Pentamethylene (Cyclopentane)	X	C	X	X	G	X	-	-	-	G
Pentane	X	E	C	X	E	X	X	E	E	E
Pentanol (Pentyl Alcohol)	E	-	E	-	-	E	-	E	E	-
Pentanone	G	X	X	G	X	X	-	-	-	X
Pentasol (Pentachlorophenol)	E	G	E	G	C	X	G	E	E	C
Pentyl Acetate (Amyl Acetate)	X	X	X	C	X	C	X	E	E	X
Pentyl Alcohol (N-Amyl Alcohol)	C	C	E	E	C	C	G	E	E	C
Pentyl Bromide (Amyl Bromide)	X	X	X	C	X	X	-	-	-	X
Pentyl Chloride (Amyl Chloride)	X	X	X	X	X	X	X	E	E	X
Pentyl Ether (Amyl Ether)	X	X	F	X	C	X	-	-	-	C
Pentylamine (Amylamine)	G	F	F	X	F	F	-	-	-	F
Perchloric Acid	C	E	C	G	X	C	X	E	E	X
Perchloroethylene (Tetrachloroethylene)	X	X	X	X	F	X	X	E	E	F
Perchloromethane (Carbon Tetrachloride)	X	X	X	X	X	X	-	-	-	X
Petroleum Crude	X	G	E	X	G	X	X	E	E	G
Petroleum Ether	X	X	C	X	E	X	X	-	-	E
Petroleum Oils	X	G	G	X	X	X	X	E	E	X
Phenbo	-	-	-	-	-	-	-	-	-	-
Phenol	C	X	C	X	X	C	X	E	E	X
Phenolsulfonic acid	G	C	C	E	C	C	X	-	-	C
Phenylamine (Aniline)	E	X	C	C	X	X	-	E	E	X
Phenylbromide (Bromobenzene)	X	-	X	-	-	X	-	-	-	-
Phenylbutane	-	-	-	-	-	-	-	-	-	-
Phenylchloride (Chlorobenzene)	X	X	X	X	X	X	-	E	E	X
Phenylethylene (Styrene)	X	X	X	X	X	X	X	-	-	X
Phenylmethane (Toluene)	X	X	X	X	X	X	-	E	E	X
Phenylmethanol (Benzyl Alcohol)	E	C	C	C	X	X	-	-	-	X
Phenylmethyl Acetate (Acetic Acid)	-	-	-	-	-	-	-	-	-	-
Phosphate Esters	E	X	X	E	X	X	X	-	-	X
Phosphoric Acid 10%	E	E	E	E	E	E	E	E	E	E
Phosphoric Acid 10% - 85%	E	G	E	E	G	G	G	E	E	G
Phosphorus Trichloride	E	X	X	E	X	X	X	E	E	X
Picric Acid, H2O Solution	G	E	E	E	E	C	G	-	-	E
Pine Oil	X	X	X	X	E	X	X	E	E	E
Pinene	X	C	X	X	C	X	X	-	-	C
Poly Chlorinated Biphenol	-	-	-	-	-	-	-	-	-	-
Polyethylene Glycol E-400	E	G	E	E	C	E	-	-	-	C
Polyol Ester	-	X	-	X	G	-	-	-	-	G
Polypropylene Glycol	E	E	E	-	E	E	-	E	E	E
Potassium Acetate	E	E	E	E	C	E	X	-	-	C
Potassium Bisulfate	E	E	E	E	E	E	G	-	-	E
Potassium Bisulfite	E	E	E	E	E	E	G	-	-	E
Potassium Carbonate	E	E	E	E	E	E	E	E	E	E
Potassium Chloride	E	E	G	E	E	E	E	E	E	E
Potassium Chromate	E	E	F	E	G	G	G	-	-	G
Potassium Cyanide	E	E	E	E	E	E	E	E	E	E

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Potassium Dichromate	E	E	G	E	E	C	G	E	E	E
Potassium Hydrate (Potassium Hydroxide)	E	-	E	-	-	C	G	E	E	-
Potassium Hydroxide	E	G	E	E	G	C	G	E	E	G
Potassium Nitrate	E	E	E	E	E	E	E	E	E	E
Potassium Permanganate, 5%	E	E	G	E	F	E	G	E	E	F
Potassium Silicate	E	E	E	E	E	E	E	-	-	E
Potassium Sulfate	E	E	E	E	E	C	G	E	E	E
Potassium Sulfide	E	E	E	E	C	G	G	-	-	C
Potassium Sulfite	E	E	C	E	E	C	G	E	E	E
Prestone Antifreeze	E	E	E	E	E	E	E	-	-	E
Producer Gas	X	G	C	X	E	X	X	-	-	E
Propane	X	E	C	X	E	X	X	E	E	E
Propanediol	E	G	E	E	E	E	E	E	E	E
Propanetriol	E	E	E	E	E	E	E	E	E	E
Propanol	E	E	E	E	E	E	E	E	E	E
Propanolamine	-	-	-	-	-	-	-	-	-	-
Propanone	E	X	C	E	X	C	G	E	E	X
Propenol	E	-	E	-	-	E	-	-	-	-
Propanediamine	E	-	F	-	G	G	-	-	-	G
Propene nitrile	X	X	-	-	X	G	-	E	E	X
Propenyl Alcohol (Allyl Alcohol)	E	E	E	E	E	E	-	E	E	E
Propenyl Anisole	X	-	X	-	X	X	-	E	E	X
Propionic Acid	E	C	G	E	C	E	X	-	-	C
Propionitrile	E	C	-	C	E	E	-	-	-	E
Propyl Acetate	C	X	X	C	X	X	X	E	E	X
Propyl Alcohol	E	E	E	E	E	E	E	E	E	E
Propyl Aldehyde	G	X	X	G	X	F	-	-	-	X
Propyl Benzene	X	X	X	-	-	X	-	-	-	-
Propyl Chloride	F	F	X	F	X	X	-	-	-	X
Propyl Ether	-	-	-	-	-	-	-	-	-	-
Propyl Nitrate	C	X	X	C	X	X	X	-	-	X
Propylene	X	X	X	X	X	X	X	-	-	X
Propylene Diamine	E	-	F	-	G	G	-	-	-	G
Propylene Glycol	E	E	E	E	E	E	E	E	E	E
Pydraul, 'E' Series	C	X	X	C	X	X	X	-	-	X
Pydraulic 'C'	X	X	X	X	X	X	X	-	-	X
Quintolubric 822 Series	-	-	-	-	-	-	-	-	-	-
Red Oil	X	F	C	F	E	X	X	E	E	E
Refrigerant 11 (Freon 11)	X	-	E	-	-	X	X	E	E	-
Refrigerant 12 (Freon 12)	X	-	E	-	-	X	E	E	E	-
Refrigerant 22 (Freon 22)	X	-	E	-	-	C	E	E	E	-
Resorcinol	E	A	G	G	C	E	G	-	-	C
Sae No. 10 Oil	X	C	X	X	E	X	X	-	-	E
Sal Ammoniac	E	E	E	E	E	E	E	E	E	E
Sea Water	E	E	E	E	E	E	E	E	E	E
Sewage	G	C	E	G	E	G	G	E	E	E
Silicate Esters	X	E	G	X	G	X	C	-	-	G
Silicate of Soda (Sodium Silicate)	E	E	E	E	E	E	E	-	-	E
Silicone Grease	E	E	E	E	E	E	E	E	E	E
Silicone Oil	E	E	E	E	E	E	E	E	E	E
Silver Nitrate	E	E	E	E	C	E	G	E	E	C
Skydrol 500 Type 2	G	X	X	E	X	X	X	-	-	X
Skydrol 500b	G	X	X	E	X	X	X	-	-	X
Skydrol 500c	G	X	X	E	X	X	X	-	-	X
Skydrol 7000 type 2	E	X	X	E	X	E	X	-	-	X

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.

KEY TO CHEMICAL RESISTANT CHART

(all data based on +68°F (+20°C) unless noted)

E Excellent G Good F Fair C Conditional I Insufficient Data X Not Recommended No Data

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Soap Solutions	E	G	E	E	E	F	X	E	E	E
Soda Ash	E	E	E	E	E	E	X	E	E	E
Soda Lime	E	G	G	E	G	E	-	-	-	G
Soda Niter	E	G	E	E	E	G	G	E	E	E
Sodium Acetate	F	C	G	E	G	F	X	E	E	G
Sodium Aluminate	E	E	E	E	E	E	G	-	-	E
Sodium Bicarbonate	E	E	E	E	E	E	E	E	E	E
Sodium Bisulfate	E	E	E	E	E	E	G	E	E	E
Sodium Bisulfite	E	E	E	E	E	E	G	E	E	E
Sodium Borate	E	E	E	E	E	E	E	E	E	E
Sodium Carbonate	E	E	E	E	E	E	E	E	E	E
Sodium Chloride	E	E	E	E	E	E	E	E	E	E
Sodium Cyanide	E	E	E	E	E	E	E	E	E	E
Sodium Dichromate	E	F	G	E	E	X	G	-	-	E
Sodium Hydrate (Sodium Hydroxide)	E	G	C	E	X	E	G	E	E	X
Sodium Hydrochlorite	G	F	E	G	F	F	G	-	-	F
Sodium Hydroxide (Caustic Soda)	E	G	C	E	X	E	G	E	E	X
Sodium Hypochlorite	C	C	G	E	C	X	F	E	E	C
Sodium Metaphosphate	G	E	C	E	E	E	E	E	E	E
Sodium Nitrate	E	G	E	E	C	G	G	E	E	C
Sodium Perborate	E	G	E	E	C	G	G	-	-	C
Sodium Peroxide	E	G	G	E	C	C	G	E	E	C
Sodium Phosphate	E	G	E	E	E	E	E	E	E	E
Sodium Silicate	E	E	E	E	E	E	E	E	E	E
Sodium Sulfate	E	E	E	E	E	C	G	E	E	E
Sodium Sulfide	E	E	E	E	E	G	G	E	E	E
Sodium Sulfite	E	E	E	E	E	G	G	E	E	E
Sodium Thiosulfate	E	E	E	E	C	G	-	E	E	C
Soybean Oil	G	E	G	C	E	X	X	-	-	E
Stannic Chloride	E	G	E	E	E	E	E	E	E	E
Stannic Sulfide	E	E	E	E	E	E	-	-	-	E
Stannous Chloride	E	E	E	G	E	E	E	E	E	E
Stannous Sulfide	E	E	E	E	E	E	-	-	-	E
Steam, below 350 Deg F	G	X	C	E	X	C	X	X	X	X
Stearic Acid	C	G	G	G	G	C	G	E	E	G
Stoddard Solvent	X	G	X	X	E	X	X	E	E	E
Styrene	X	X	X	X	X	X	X	F	F	X
Sulfamic Acid	E	G	E	E	C	G	-	-	-	C
Sulfur	E	E	E	E	X	X	X	E	E	X
Sulfur Chloride	X	E	-	E	C	X	X	-	-	C
Sulfur Dioxide	C	C	C	E	X	C	G	-	G	X
Sulfur Trioxide, Dry	G	X	X	E	X	C	X	X	X	X
Sulfuric Acid 60% (200°F)	E	X	G	E	G	X	X	X	X	G
Sulfuric Acid, Conc.	X	X	X	X	X	X	X	F	F	X
Sulfuric Acid, Fuming	X	X	X	X	X	X	X	X	X	X
Sulfuric Acid, 25%	G	C	E	E	C	E	F	E	E	C
Sulfuric Acid, 25%-50%	G	X	G	E	C	G	F	E	E	C
Sulfuric Acid, 50%-96%	C	X	C	X	X	C	X	G	G	X
Sulfurous Acid, 10%	E	C	E	E	E	G	G	E	E	E
Sulfurous Acid, 10%-75%	E	C	E	E	F	G	G	E	E	F
Sutan	-	-	-	-	-	-	-	-	-	-
T-Butyl Amine	C	X	X	C	C	X	-	-	-	C
Tall Oil	X	C	F	X	E	X	X	-	-	E
Tallow	X	G	F	E	E	X	X	E	E	E
Tannic acid	E	E	E	E	E	E	G	E	E	E
Tar	X	X	-	X	X	X	X	X	F	X

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Tar Bituminous	X	C	X	X	G	X	X	-	-	G
Tartaric Acid	G	E	E	G	E	E	G	E	E	E
Tellone 2	-	-	-	-	-	C	-	-	-	-
Tertiary Butyl Alcohol	C	C	C	C	C	C	G	-	-	C
Terpineol	C	-	X	-	-	X	X	-	-	-
Tertiary Butyl Amine	C	X	X	C	C	X	-	-	-	C
Tertiary Butyl Mercaptan	X	X	X	X	X	X	X	-	-	X
Test Entry	-	-	-	-	-	-	-	-	-	-
Test Entry 1	-	-	-	-	-	-	-	-	-	-
Tetrachlorobenzene	X	X	X	X	X	X	-	-	-	X
Tetrachloroethane	X	X	X	X	X	X	X	F	F	X
Tetrachloroethylene	X	X	X	X	C	X	X	F	F	C
Tetrachloromethane	X	X	X	X	X	X	-	E	E	X
Tetrachloronaphthalene	X	X	X	X	X	X	-	E	E	X
Tetraethylene glycol	E	E	E	E	E	E	-	-	-	E
Tetraethylorthosilicate	E	E	-	E	E	X	-	-	-	E
Tetrahydrofuran (thf)	C	X	X	X	X	X	X	-	-	X
Tin Chloride	E	C	C	E	E	E	-	E	E	E
Titanium Tetrachloride	X	C	X	X	C	X	X	-	-	C
Toluene	X	X	X	X	X	X	X	E	E	X
Toluidine	X	X	X	X	C	X	-	E	F	C
Toluol (Toluene)	X	X	X	X	X	X	X	E	E	X
Transformer Oil	X	C	C	X	C	X	X	E	E	C
Transmission 'A' Oil	X	C	C	X	E	X	-	-	-	E
Tri(2-Hydroxyethyl) Amine (Triethanolamine)	E	C	C	E	G	C	-	-	-	G
Tributyl Phosphate	G	-	X	G	F	C	X	-	-	F
Tributylamine	E	-	F	-	G	G	-	-	-	G
Trichloroacetic Acid	C	C	X	C	C	C	X	-	-	C
Trichlorobenzene	X	X	X	X	C	X	X	F	F	C
Trichloroethane	X	X	X	X	X	X	X	-	-	X
Tichloroethylene	X	X	X	X	X	X	X	F	F	X
Trichloromethane	X	X	X	X	X	X	X	F	F	X
Trichlorotoluene (Benzotrichloride)	-	X	X	E	X	X	-	-	-	X
Tricresyl Phosphate	E	X	X	E	X	X	X	-	-	X
Triethanolamine	E	C	C	E	C	C	G	E	E	C
Triethylamine	G	G	E	E	E	G	X	-	-	E
Triethylene Glycol	E	E	E	E	C	E	-	E	E	C
Trihydroxybenzoic Acid	C	C	G	C	C	E	-	-	-	C
Trimethyl Pentane (mixed)	X	G	C	X	E	X	X	-	-	E
Trimethyl Pentene	-	-	-	-	-	-	-	-	-	-
Trimethylamine	E	E	E	C	C	E	-	-	-	C
Trisodium Phosphate	E	E	E	E	E	E	E	E	E	E
Tritoyl Phosphate	E	C	C	E	X	X	X	-	-	X
Tung Oil	C	C	C	X	E	X	X	E	E	E
Tung Oil (China Oil)	C	C	C	X	E	X	X	E	E	E
Turpentine	X	X	X	X	E	X	X	E	E	E
Unsymmetrical Dimethyl Hydrazine (Udmh)	E	C	E	E	C	E	X	-	-	C
Undecyl Alcohol	E	E	E	E	E	E	-	-	-	E
Urea (Carbammide)	E	G	E	E	G	E	-	E	E	G
Urethane Formulations	-	-	-	-	-	-	-	-	-	-
Uric Acid	E	E	E	E	C	E	-	-	-	C
Varnish	X	X	X	X	G	X	X	E	E	G
Vegetable Oils	C	C	G	F	E	X	X	E	E	E
Versilube f44	E	E	E	E	E	E	E	-	-	E

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.

KEY TO CHEMICAL RESISTANT CHART

(all data based on +68°F (+20°C) unless noted)

E Excellent **G** Good **F** Fair **C** Conditional **I** Insufficient Data **X** Not Recommended No Data

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
Versilube f55	E	E	E	X	E	E	E	-	-	E
Vinegar (Acetic Acid)	E	G	E	E	G	G	G	E	E	G
Vinegar Acid (Vinegar)	E	-	E	-	-	G	-	E	E	-
Vinyl Acetate	E	C	F	G	C	X	X	E	E	C
Vinyl Benzene	X	X	X	X	C	X	X	F	F	C
Vinyl Chloride	X	X	X	C	X	X	-	E	E	X
Vinyl Cyanide	X	X	G	X	X	G	F	E	E	X
Vinyl Ether (Divinyl Ether)	X	-	G	-	G	X	-	-	-	G
Vinyl Styrene	-	-	-	-	-	-	-	-	-	-
Vinyl Toluene	X	X	X	X	X	X	-	-	-	X
Vinyl Trichloride (Trichloroethane)	X	X	X	X	X	X	-	-	-	X
Vital, 4300,5310	-	-	-	-	-	-	-	-	-	-
VM & Naphtha	X	F	X	X	G	X	X	-	-	G
Water	E	G	E	E	E	E	C	E	E	E
Water, Boiling	E	G	E	E	G	E	-	-	-	G
Water, Soda	-	-	-	-	-	-	-	E	E	-
Wemco C	X	C	X	X	E	X	X	-	-	E
Whiskey	E	E	E	E	E	E	E	E	E	E
White Oil	X	G	C	X	E	X	X	E	E	E
White Pine Oil	X	X	X	X	C	X	X	-	-	C
Wines	E	E	E	E	E	E	E	E	E	E
Wood Alcohol (Methanol)	C	E	E	E	C	E	E	E	E	C
Wood Oil	C	C	C	X	E	X	X	E	E	E
Xenon	E	E	E	E	E	E	E	-	-	E
Xylene, Xylon	X	X	X	X	X	X	X	F	F	X
Xylidine	G	X	X	G	C	X	X	-	-	C
Zeolites	E	E	E	E	E	E	E	-	-	E
Zinc acetate	E	C	-	E	G	E	X	-	-	G
Zinc carbonate	E	E	E	E	E	E	-	-	-	E
Zinc chloride	E	E	E	E	E	E	E	E	E	E
Zinc chromate	E	E	G	E	C	E	-	-	-	C
Zinc sulfate	E	E	E	E	E	E	G	E	E	E
0-Aminotoluene (0-methylaniline)	C	X	X	C	X	X	-	-	-	X
1 Undecanol	E	E	E	E	E	E	E	E	G	E
1-Amino-2-Propanol (Isopropanolamine)	E	E	F	E	C	G	-	-	-	C
1-Aminobutane (Butylamine)	C	X	X	C	C	X	X	-	-	C
1-Aminopentane (Amylamine)	G	C	F	X	F	F	-	-	-	F

CHEMICAL OR MATERIAL CONVEYED	COMPOUND									
	CIIR	CR	CSM	EPDM	NBR	NR	SBR	XLPE	UHMWPE	T629AA
1-Bromo-2-Methyl Propane (Isobutyl bromide)	X	X	X	X	X	X	-	-	-	X
1-Bromo-3-Methyl Butane (Isoamyl bromide)	X	X	X	X	X	X	-	-	-	X
1-Bromobutane (N-Butyl Bromide)	X	X	X	X	X	X	-	-	-	X
1-Chloro-2-Methyl Propane (Isobutyl Chloride)	X	X	X	X	X	X	-	-	-	X
1-Chloro-3-Methyl butane (Isoamyl chloride)	X	X	X	X	X	X	-	-	-	X
1-Decanol	X	X	C	X	E	X	-	E	E	E
1-Hendecanol (Undecanol)	E	E	E	E	E	E	-	-	-	E
1,4-Dioxane	C	X	X	C	X	X	-	E	-	X
2(2Aminoethylamino) Ethanol (N-(Aminoethyl)ethanolamine)	E	-	G	-	-	G	-	-	-	-
2(2Ethoxyethoxy) Ethanol (Carbitol)	C	C	C	C	C	C	G	-	-	C
2(2Ethoxyethoxy) Ethyl Acetate (Carbitol Acetate)	G	X	G	X	X	X	X	-	-	X
2-Aminoethanol (Ethanolamine)	C	C	C	E	C	C	F	-	-	C
2-Chloro-1-Hydroxy-Benzene (0-Chlorphenol)	X	X	X	X	X	X	-	-	-	X
2-Chlorophenol	X	X	X	X	X	X	X	-	-	X
2-Chloropropane	X	X	X	X	X	X	X	-	-	X
2-Ethoxyethanol	C	X	X	C	C	X	X	E	E	C
2-Ethoxyethyl Acetate	C	X	X	G	X	C	-	E	E	X
2-Ethyl(Butyraldehyde)	G	-	X	-	X	X	-	-	-	X
2-Ethyl-1-Hexanol	C	C	C	C	C	G	G	E	E	C
2-Ethylhexanoic Acid (Ethylhexoic Acid)	F	-	G	-	F	F	-	-	-	F
2-Ethylhexyl Acetate	E	-	G	-	X	X	-	C	C	X
2-Octanone (Methyl Hexyl Ketone)	G	C	-	G	X	X	-	-	-	X
2,4-Di-Sec--Pentylphenol	-	-	-	-	-	-	-	-	-	-
3-Bromopropene (Allyl Bromide)	X	X	X	X	X	X	-	-	-	X
3-Chloro-2-Methyl Propane	-	-	-	-	-	-	-	-	-	-
3-Chloropropene	C	X	X	X	C	X	E	E	G	C
3-Coal Oil	X	G	F	X	E	X	-	-	-	E
4-Hydroxy-4-Methyl-2-Pentanone (Diacetone Alcohol)	E	F	C	E	X	X	X	E	E	X

Because we continually examine ways to improve our products, we reserve the right to alter specifications or discontinue products without prior notice.